CI/SfB (43) Vv1 CAW M60 Uniclass L68245:P7103

December 2009

Water Based Epoxy Primer

KEY BENEFITS SUMMARY

- Good penetrating properties
- Formulated specifically for use beneath the Tremco range of screeds and coatings

PRODUCT INFORMATION

Description

Tremco CS120 is based on a blend of water based epoxy resin and curing agent binder giving the low viscosity characteristics necessary to wet the substrate, giving good penetration properties prior to overlaying with epoxy coatings, flooring compounds, etc.

Typical Uses

This product can be used as a general purpose primer beneath the Tremco range of industrial floor screeds onto porous substrates. May also be used under cementitious screeds to reduce the porosity of the substrate prior to using Treadfast Epoxyprime Plus.

Can be used as a moisture vapour suppressant. Please refer to Tremco Technical Department for a written Specification

Packaging

10 kg (2 component kit)

Colour

Pale Yellow/Clear



Coverage Rate

Up to 6 to 8 m² per kg per coat

Cure Time

Working time: 30 to 40 minutes Walk on / overcoat after 12 to 24 hours at ambient temperatures.

Storage

Store in dry shaded conditions between +5 °C and +25 °C.

Shelf Life

12 months when stored as recommended in original unopened packaging.

Health & Safety Precautions

Product Health and Safety Data Sheets must be read and understood before use.

USAGE GUIDELINES

Standards

All aspects of the installation must be in accordance with the requirements of BS8204, BS8203 (Installation of Resilient floorcoverings) or BS5325 (Installation of Textile floorcoverings) and supplementary specifications.

Preparation

The substrate should be clean, free from laitance, oil, grease or other agents which may impair adhesion. Techniques should include (depending on degree of contamination) acid etching, light mechanical scabbling, blasting, grinding or degreasing.



CS120

Tremco illbruck Limited Coupland Road Hindley Green, Wigan WN2 4HT UK Tel: 01942 251400 Fax:01942 251410 Email: uk.info@tremco-illbruck.com

Email: uk.into@tremco-illbruck.com Website: www.tremco-illbruck.co.uk

Mixing

Tremco CS120 is supplied in preweighed packs. Add all the contents of Curing Agent Component B to Epoxy Resin Component A and mix thoroughly. Once mixed the primer should be immediately applied.

Application

Tremco CS120 is applied to the prepared substrates by roller or brush, ensuring a continuous film. Avoid overapplication and puddles. Porous floors may require two coats.

Technical Service

Tremco illbruck has a team of experienced Technical Sales
Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

Guarantee / Warranty

Tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco illbruck written instructions and (b) in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.







