

CI/SfB	(43)	Yt3
CAW Z20		
Uniclass L6739:P7102		
July 2012		

### KEY BENEFITS SUMMARY

- Strong permanent bond
- Compatible with a wide range of vinyls including the highly plasticised types
- Guaranteed no serration marks
- Can be applied direct to clean impervious surfaces
- Safe, clean, more efficient installation
- Thermo-welding same day with dry bond method
- Solvent free, low toxicity and non-flammable
- Meets existing low VOC requirements

### PRODUCT INFORMATION

#### Description

Tremco SF108 Pressure Sensitive Acrylic Adhesive is a pressure sensitive adhesive for vinyl floor and wall coverings.

#### Usage / Purpose

Tremco SF108 Pressure Sensitive Acrylic Adhesive is used for:

- bonding PVC floor, wall and ceiling coverings
- also refer to Tremco SF108 Pressure Sensitive Acrylic Adhesive data sheet for rubber floor coverings.

#### LIMITATIONS

Tremco SF108 Pressure Sensitive Acrylic Adhesive is not recommended for wet areas unless all joints are sealed.

Not recommended for wall applications in wet rooms, bathrooms or shower rooms. Tremco SF108 adhesive should never be exposed to humidity greater than 75%.

#### Colour

White (wet), Transparent (dry).

#### Environmental Considerations

Tremco SF108 Pressure Sensitive Acrylic Adhesive is solvent free, has low toxicity and is non-flammable. Will not promote bacteria growth in wet or dry state.

#### Packaging

5 and 15 litre polythene pails

#### Availability

Direct from Tremco illbruck (see back of leaflet for address and telephone details) or via approved distributors.

### TECHNICAL INFORMATION

#### Composition

A one part acrylic co-polymer emulsion.

#### Performance (Typical Values)

##### OPEN TIME

3 days (provided the surface is kept free of dust and contamination)

##### SERVICE TEMPERATURE RANGE

-20°C to +60°C

#### CHARACTERISTICS (Typical Values)

##### DENSITY (at +25°C)

1.02 - 1.04

##### SOLIDS CONTENT BY WEIGHT

60% ± 1%

##### FLASH POINT

None

### USAGE GUIDELINES

#### Standards

All aspects of the installation must be in accordance with the requirements of BS8204, BS8203 (Installation of Resilient floorcoverings) or BS5325 (Installation of Textile floorcoverings) and supplementary specifications.

#### Surface Preparation

- Site conditions MUST comply with British Standards CP 102, BS 8203, BS 5325 and supplementary specifications.
- The surfaces must be sound, clean, dry and free from oil, grease, paint, excessive dust and other contaminants liable to impair adhesion.
- Concrete and sand/cement screeds must be fully cured and free from laitance.
- Direct to earth subfloors must incorporate an efficient damp proof membrane.
- Underfloor heating must have been fully commissioned as per manufacturers instructions and must be switched off 48 hours before and during installation. The heating should be switched on 48 hours after completion but then only gradually as per the commissioning schedule. Consult the Technical Department for a full specification.

#### Priming

- Porous surfaces should be primed with Tremco SF108 Pressure Sensitive Acrylic Adhesive adhesive diluted 1:1 with clean water, by paint roller and allow to dry.

# SF108

Tremco illbruck Limited  
Coupland Road  
Hindley Green, Wigan WN2 4HT UK  
Tel: 01942 251400  
Fax: 01942 251410  
Email: uk.info@tremco-illbruck.com  
Website: www.tremco-illbruck.co.uk

## Method of Application

The adhesive must be thoroughly stirred before use.

### PVC FLOOR COVERING

- Spread the adhesive evenly using a notched trowel (1.5 mm x 5 mm for PVC floor coverings).
- Immediately roll with a long handled paint roller which has been wetted with the adhesive. Smooth out the trowel serration marks to give a uniform smooth appearance. Allow the adhesive to dry until it takes on a clear appearance.
- On smooth even subfloors the adhesive can be applied direct with a paint roller if a uniform coating can be achieved.
- Place the floor covering accurately in position and roll with a 68 kg flooring roller in both directions.

### Traditional Application For Porous Substrates

- Spread with a 1.5 mm x 5 mm notched trowel and lay flooring into semi wet adhesive.

### PVC WALL CLADDING (POSITIVE PRESSURE CLEAN ROOMS)

- For negative pressure clean rooms, consult Tremco illbruck's Technical Department.
- Apply to clean, dry plaster or plasterboard.
- Prime the areas of plastered wall with Tremco SF108 Pressure Sensitive Acrylic Adhesive adhesive diluted 1:1 with clean water and allow to dry.
- Prime the areas of plastered ceiling with a neat coat of Tremco SF108 Pressure Sensitive Acrylic Adhesive and allow to dry.

- Spread Tremco SF108 Pressure Sensitive Acrylic Adhesive with a paint roller to the prepared surfaces and allow to dry. The adhesive will change from a white colour to translucent.
- Carefully place the pre-fitted PVC wall cladding into position on the DRY adhesive and firm in. Roll with a flooring grade hand roller from the centre outwards to exclude air. A second rolling will be necessary.

### DOUBLE STICK BONDING

- With certain vinyls it may be necessary to double stick at the top edge to give extra support on the horizontal and at pressure points.
- Apply Tremco SF115 Contact Adhesive to the back of the vinyl, approximately 150 mm deep at the edge and to the corresponding points on the wall including any pressure points, and allow it to become touch dry.
- Carefully place on to the DRY Tremco SF108 Pressure Sensitive Acrylic Adhesive adhesive and firm in.

### Coverage Rate

Up to 7.5 m<sup>2</sup> per litre.

### Cleaning

When not using the paint roller wrap it in a polythene bag. Exclude air to prevent the adhesive from setting on the roller. Stand the roller upright so as not to subject it to any pressure. The roller will then be suitable for further application. Clean tools, etc., with warm water.

### Health & Safety Precautions

Product Health and Safety Data Sheet must be read and understood before use.

## Storage

Store in shaded dry conditions at a minimum temperature of +5°C. DO NOT ALLOW TO FREEZE.

## Shelf Life

9 months when stored as recommended in original unopened containers.

## Technical Service

Tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

## Guarantee/Warranty

Tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with Tremco illbruck written instructions and (b) in any application recommended by Tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

Tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.