

SX070

FEATHER FINISH COMPOUND



KEY BENEFITS SUMMARY

- Short setting and cure time, facilitating a fast track program and minimising disruption
- Can be applied over well bonded thin film adhesive residues
- Can be used to repair ridges and depressions up to 12 mm, or to achieve a true feather edge
- Does not require a primer prior to application
- Excellent adhesion to a wide range of common flooring substrates, including: concrete, sand/cement screeds, plywood, glazed and unglazed floor tiles, etc.

PRODUCT INFORMATION

Description

SX070 is a rapid drying feather finish compound for interior applications.

Usage/Purpose

Ideal for smoothing and repairing the subfloors prior to the installation of a floor covering.

Colour

Grey powder

Packaging

10 kg bucket

Standards

All aspects of the installation must be in accordance with the requirements of BS 8204, BS 8203 (Installation of Resilient Floor Coverings) or BS 5325 (Installation of Textile Floor Coverings) and supplementary specifications.

Moisture Testing

(in accordance with British Standards 8203)

- Suitable for application on substrates with <75 % RH.
- It is recommended that a moisture test is conducted prior to the application of SX070. For further details or to arrange for a moisture test please contact tremco illbruck Technical Services.

Preparation

- Ensure all surfaces to be coated are clean, dry, frost free and free from grease, oil, dirt, dust, loose friable material and any other contaminants (coating, laitance, etc).
- Any surface hardener or curing compounds should be thoroughly removed prior to the application of SX070.

Priming

- Not usually required on porous substrates. Non porous substrates should be primed with CS100 Epoxy Primer.

Protection on Completion

Ensure the screed is not subject to draughts during the first 6 hours of curing as this may lead to cracking and crazing. Tape up doorways with polythene to prevent air movement.

Prevent contamination by following trades (e.g. plastering), including water spillage.

Cleaning

Immediately after use all tools and equipment should be cleaned with water. Cured material can be removed mechanically or by acid etching.

Please note

Not suitable for use at ambient temperatures below +5°C or over +30°C.

Health & Safety Precautions

Safety Data Sheet must be read and understood before use.

Contract Application

tremco illbruck Limited has a network of nationwide approved installers and provides full technical assistance on specific site applications.

Availability

Direct from tremco illbruck (see back of leaflet for address and telephone details), or via local and national distributors.

Technical Service

tremco illbruck has a team of experienced Technical Sales Representatives who provide assistance in the selection and specification of products. For more detailed information, service and advice, please call Customer Services on 01942 251400.

SX070

FEATHER FINISH COMPOUND

TREMCO

Guarantee/Warranty

tremco illbruck products are manufactured to rigid standards of quality. Any product which has been applied (a) in accordance with tremco illbruck written instructions and (b) in any application recommended by tremco illbruck, but which is proved to be defective, will be replaced free of charge.

No liability can be accepted for the information provided in this leaflet although it is published in good faith and believed to be correct.

tremco illbruck Limited reserves the right to alter product specifications without prior notice, in line with Company policy of continuous development and improvement.

TECHNICAL DATA

PROPERTY	RESULT
Composition	A blend of special cements, graded fillers and modified polymers
Open Time/Workability (at +20°C)	15 minutes
Pot Life (at 20°C)	20 minutes
Coverage	An average thickness of 1 mm will give a coverage rate of 14 m ² per mix. Up to 50 m ² coverage may be achieved when used as a true feather edge.
Cure Time (at 20°C)	Floor Covering: After 1 hour Full Traffic: After 24 hours
Storage	Store in dry shaded conditions between +5°C and +25°C
Shelf Life	6 months when stored as recommended in original unopened packaging



tremco illbruck - A Company approved to:

tremco illbruck Limited, Coupland Rd,
Hindley Green, Wigan, WN2 4HT, UK.
Tel: +44 (0)1942 251400
Fax: 01942 251410
Email: uk.info@tremco-illbruck.com
Website: www.tremco-illbruck.co.uk

**tremco
illbruck**
www.tremco-illbruck.com

2015-02 v01